



# QUICK SPEC

## GYP SUM (DensDeck & SecuRock) – HYDROSTOP® PREMIUMCOAT®

NOTE: The following “Quick Spec” is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project.

- Method**
  - Use GAF Roof Brush to apply HydroStop® PremiumCoat® Foundation Coat
  - Spray, roller, or brush apply HydroStop® PremiumCoat® Finish Coat
- Requirements**
  - Roof must be clean, dry, and tight.
  - Adhesion test required to ensure proper adhesion to substrate(s).
  - If mechanically attached, plates must be encapsulated with Butter Grade Flashing.
  - All seams must be treated Butter Grade w/fabric OR HydroStop® PremiumCoat® Foundation Coat w/fabric.
  - Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours.
- Application Instructions**
  - GAF recommends that the surface temperature be at or less than 105°F (40°C) during application.
  - 1. Ensure roof is free of dirt, debris, oil, and other contaminants that could negatively affect adhesion.
  - 2. In most cases, no primer is required for this substrate.
  - 3. Before applying the HydroStop® PremiumCoat® System, an adhesion test is required to ensure an adhesion of a minimum of 2.0 PLI. Test patches to be applied with system rates listed below:
  - 4. Apply HydroStop® PremiumCoat® Foundation Coat and HydroStop® PremiumCoat® Finish Coat per the chart below.

<b>GYP SUM (DensDeck &amp; SecuRock) HYDROSTOP® PREMIUMCOAT® SYSTEM</b>											
<b>Warranty Term</b>	<b>Foundation Coat (with fabric)</b>		<b>Finish Coat</b>					<b>System</b>		<b>Warranty</b>	
	<b>Total (Gal/Sq)</b>	<b>DFT* (mils)</b>	<b>1st Coat (Gal/Sq)</b>	<b>2nd Coat (Gal/Sq)</b>	<b>3rd Coat (Gal/Sq)</b>	<b>Total (Gal/Sq)</b>	<b>DFT* (mils)</b>	<b>Total (Gal/Sq)</b>	<b>DFT* (mils)</b>	<b>Emerald Pledge™</b>	<b>Diamond Pledge™</b>
10 Year	2.5	27	0.75	0.75		1.5	13	4.0	40	Yes	Yes
15 Year	2.5	27	1.0	1.0		2.0	17	4.5	44		
20 Year	2.5	27	1.0	1.0	1.0	3.0	25	5.5	52		
25 Year	2.5	27	1.5	1.5	1.0	4.0	33	6.5	60		

\* DFT (Dry Film Thickness) is rounded to nearest mil. Actual DFT will vary dependent on substrate profile, application technique & waste factor. Primer/Base is not included in DFT calculations.