



QUICK SPEC

PVC

ROOF MATE™

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project.

- | | |
|---------------------------------|--|
| Method | <ul style="list-style-type: none"> Spray, roller, or brush |
| Requirements | <ul style="list-style-type: none"> Moisture survey recommended. Roof must be clean, dry, and tight. Adhesion test required to ensure proper adhesion to substrate(s). Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours. GAF recommends that the surface temperature be at or less than 110°F (43°C) during application. |
| Application Instructions | <ol style="list-style-type: none"> Before applying Roof Mate™, an adhesion test is required to ensure an adhesion minimum of 2.0 PLI. Test patches to be applied with rates listed below. Conduct moisture survey and remove/replace all wet areas. Repair membrane including seams, penetrations, flashings, curbs, and terminations with like materials. Power-wash roof. United Cleaning Concentrate (UCC) is recommended to clean the roof. Allow the roof to completely dry. Prime using Unisil Primer. Treat all roof penetrations, drains, curbs, and scuppers. Treat all seams. Apply coating per the chart below: |

PVC ROOF MATE™								
Warranty Term	Coating				Total		Warranty	
	Product (Choose one)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	3rd Coat (Gal/Sq)	Gal/Sq	DFT* (mils)	Emerald Pledge	Diamond Pledge
10 Year	Roof Mate™ & QS	1.50	1.50		3.00	26	Yes	No
	Roof Mate™ HT	1.50	1.50		3.00	25		
	Roof Mate™ TCM	1.00	1.50		2.50	23		
15 Year	Roof Mate™ & QS	1.50	1.50	1.00	4.00	34	Yes	No
	Roof Mate™ HT	1.50	1.50	1.00	4.00	33		
	Roof Mate™ TCM	1.00	1.50	1.00	3.50	33		

* DFT (Dry Film Thickness) is rounded to nearest mil and is theoretical. Actual DFT will vary dependent on substrate profile, application technique & waste factor.